



BLEND DR 37

Neutral in appearance from the inside, this metallic film provides the dual benefits of exterior privacy while enjoying interior views. It provides a highly reflective exterior shine for increased privacy and glare reduction – significantly increasing the solar performance of your existing glass.

BENEFITS

- Provides glare reduction and privacy options.
- Exterior reflectivity changes the appearance of existing glass to provide a more uniform look.
- Very high solar heat reduction.
- Blocks 99% of harmful UV rays.



BLEND DR 37

PERFORMANCE DATA

	SINGLE PANE	DUAL PANE
VISIBLE LIGHT:		
Visible Light Transmitted	40%	36%
Reflected Exterior	13%	20%
Reflected Interior	10%	11%

	SINGLE PANE	DUAL PANE
SOLAR ENERGY:		
Energy Transmitted	39%	32%
Energy Reflected	18%	22%
Energy Absorbed	43%	46%
UV Rejection	99%	99%
Total Solar Energy Rejected (TSER)	51%	46%
Infrared Heat Rejected	67%	67%
Shading Coefficient	0.58	0.64
Solar Heat Gain Coefficient	0.49	0.54
U Factor	0.98	0.47
Emissivity	0.75	0.75
Glare Reduction	56%	56%

The performance data above was tested according to ASTM & AIMCAL standards. All values represented are as applied on 1/8" (3mm) glass. Specific technical information can be found at WWW.XPEL.COM. For additional information contact SUPPORT@XPEL.COM.

WARRANTY INFORMATION

VISION Films are backed by a comprehensive warranty.



BLEND DR 27

Neutral in appearance from the inside, this metallic film provides the dual benefits of exterior privacy while enjoying interior views. It provides a highly reflective exterior shine for increased privacy and glare reduction – significantly increasing the solar performance of your existing glass.

BENEFITS

- Provides glare reduction and privacy options.
- Exterior reflectivity changes the appearance of existing glass to provide a more uniform look.
- Very high solar heat reduction.
- Blocks 99% of harmful UV rays.



BLEND DR 27 PERFORMANCE DATA

	SINGLE PANE	DUAL PANE
VISIBLE LIGHT:		
Visible Light Transmitted	33%	29%
Reflected Exterior	20%	27%
Reflected Interior	13%	14%

	SINGLE PANE	DUAL PANE
SOLAR ENERGY:		
Energy Transmitted	29%	23%
Energy Reflected	26%	29%
Energy Absorbed	45%	48%
UV Rejection	99%	99%
Total Solar Energy Rejected (TSER)	61%	54%
Infrared Heat Rejected	80%	80%
Shading Coefficient	0.45	0.55
Solar Heat Gain Coefficient	0.39	0.46
U Factor	0.99	0.47
Emissivity	0.45	0.75
Glare Reduction	65%	65%

The performance data above was tested according to ASTM & AIMCAL standards. All values represented are as applied on 1/8" (3mm) glass. Specific technical information can be found at WWW.XPEL.COM. For additional information contact SUPPORT@XPEL.COM.

WARRANTY INFORMATION

VISION Films are backed by a comprehensive warranty.



BLEND DR 17

Neutral in appearance from the inside, this metallic film provides the dual benefits of exterior privacy while enjoying interior views. It provides a highly reflective exterior shine for increased privacy and glare reduction – significantly increasing the solar performance of your existing glass.

BENEFITS

Offers extreme glare reduction and privacy options.

Exterior reflectivity changes the appearance of existing glass to provide a more uniform look.

Very high solar heat reduction.

Blocks 99% of harmful UV rays.



BLEND DR 17

PERFORMANCE DATA

	SINGLE PANE	DUAL PANE
VISIBLE LIGHT:		
Visible Light Transmitted	13%	11%
Reflected Exterior	45%	46%
Reflected Interior	21%	23%

	SINGLE PANE	DUAL PANE
SOLAR ENERGY:		
Energy Transmitted	11%	8%
Energy Reflected	46%	43%
Energy Absorbed	43%	49%
UV Rejection	99%	99%
Total Solar Energy Rejected (TSER)	79%	69%
Infrared Heat Rejected	90%	90%
Shading Coefficient	0.26	0.36
Solar Heat Gain Coefficient	0.21	0.31
U Factor	0.99	0.47
Emissivity	0.75	0.75
Glare Reduction	87%	86%

The performance data above was tested according to ASTM & AIMCAL standards. All values represented are as applied on 1/8" (3mm) glass. Specific technical information can be found at WWW.XPEL.COM. For additional information contact SUPPORT@XPEL.COM.

WARRANTY INFORMATION

VISION Films are backed by a comprehensive warranty.



BLEND DR 7

Neutral in appearance from the inside, this metallic film provides the dual benefits of exterior privacy while enjoying interior views. It provides a highly reflective exterior shine for increased privacy and glare reduction – significantly increasing the solar performance of your existing glass.

BENEFITS

- Offers extreme glare reduction and privacy options.
- Exterior reflectivity changes the appearance of existing glass to provide a more uniform look.
- Very high solar heat reduction.
- Blocks 99% of harmful UV rays.



BLEND DR 7

PERFORMANCE DATA

	SINGLE PANE	DUAL PANE
VISIBLE LIGHT:		
Visible Light Transmitted	6%	5%
Reflected Exterior	43%	47%
Reflected Interior	8%	8%
SOLAR ENERGY:		
Energy Transmitted	7%	5%
Energy Reflected	46%	44%
Energy Absorbed	47%	51%
UV Rejection	99%	99%
Total Solar Energy Rejected (TSER)	82%	70%
Infrared Heat Rejected	92%	92%
Shading Coefficient	0.21	0.35
Solar Heat Gain Coefficient	0.18	0.30
U Factor	0.98	0.47
Emissivity	0.75	0.75
Glare Reduction	94%	94%

The performance data above was tested according to ASTM & AIMCAL standards. All values represented are as applied on 1/8" (3mm) glass. Specific technical information can be found at WWW.XPEL.COM. For additional information contact SUPPORT@XPEL.COM.

WARRANTY INFORMATION

VISION Films are backed by a comprehensive warranty.