



DAYLIGHT 50

More reflective than CLEAR VIEW, this NEUTRAL film features a blend of metals that create a less shiny appearance than conventional metal films.

BENEFITS

Reduces the heat load from existing glass surfaces.

Increases the shine of existing glass surfaces, while providing additional comfort to any room.

Blocks 99% of harmful UV rays.



DAYLIGHT 50

PERFORMANCE DATA

	SINGLE PANE	DUAL PANE
VISIBLE LIGHT:		
Visible Light Transmitted	52%	44%
Reflected Exterior	12%	19%
Reflected Interior	12%	13%

	SINGLE PANE	DUAL PANE
SOLAR ENERGY:		
Energy Transmitted	51%	37%
Energy Reflected	10%	16%
Energy Absorbed	39%	47%
UV Rejection	99%	99%
Total Solar Energy Rejected (TSER)	43%	38%
Infrared Heat Rejected	48%	48%
Shading Coefficient	0.66	0.72
Solar Heat Gain Coefficient	0.57	0.62
U Factor	1.07	0.49
Emissivity	0.89	0.89
Glare Reduction	46%	46%

The performance data above was tested according to ASTM & AIMCAL standards. All values represented are as applied on 1/8" (3mm) glass. Specific technical information can be found at WWW.XPEL.COM. For additional information contact SUPPORT@XPEL.COM.

WARRANTY INFORMATION

VISION Films are backed by a comprehensive warranty.



DAYLIGHT 28

More reflective than CLEAR VIEW, this neutral film features a blend of metals that create a less shiny appearance than conventional metal films.

BENEFITS

- Reduces the heat load from your current glass.
- Increases the shine of your current glass, while providing added comfort to any room.
- Blocks 99% of harmful UV rays.



DAYLIGHT 28

PERFORMANCE DATA

VISIBLE LIGHT:	SINGLE PANE	DUAL PANE
Visible Light Transmitted	25%	22%
Reflected Exterior	26%	32%
Reflected Interior	26%	36%

SOLAR ENERGY:	SINGLE PANE	DUAL PANE
Energy Transmitted	23%	16%
Energy Reflected	23%	26%
Energy Absorbed	54%	58%
UV Rejection	99%	99%
Total Solar Energy Rejected (TSER)	64%	51%
Infrared Heat Rejected	76%	76%
Shading Coefficient	0.41	0.56
Solar Heat Gain Coefficient	0.36	0.49
U Factor	1.04	0.48
Emissivity	0.84	0.83
Glare Reduction	74%	80%

The performance data above was tested according to ASTM & AIMCAL standards. All values represented are as applied on 1/8" (3mm) glass. Specific technical information can be found at WWW.XPEL.COM. For additional information contact SUPPORT@XPEL.COM.

WARRANTY INFORMATION

VISION Films are backed by a comprehensive warranty.